

Rigid Staking Compound Epoxy Adhesive

Technical Product Bulletin

PRODUCT DESCRIPTION:

STEEL-BOND is a two part, heat-resistant and low exotherm, epoxy adhesive formulation. It is a 100% solid epoxy adhesive, with superior chemical resistance and shear strength.

STEEL-BOND contains a thixotropic agent which impedes thinning out of the material during heat cure when properly mixed and cured

PRODUCT DESCRIPTION:

Appearance	Amber
Cure Type	Room temperature or Heat cure
Benefits	<ul style="list-style-type: none"> • Room temperature or heat cure • Tough enamel like cure • Bonds variety of substrates • Weather resistant
Mix Ratio by weight	100:100 / Resin:Hardener
Substrates	Metals, glass, ceramics, wood and many plastic
Operating Temperature	-40 to 163 °C
Typical Application	Staking components, bonding, laminating and repair applications

CURE SCHEDULE:

20 min`	@ 177°C
30 min	@ 121°C
80 min	@ 93°C
4 to 6 Hours	@ 65°C

UNCURED PROPERTIES:

Specific Gravity, mixed	1.07
Reactive solids contents, %	100
Pot Life	60 minutes

MISC PROPERTIES:

Shelf life	1 year
Glass Transition Temp, Tg	93°C
Hardness, Shore D	78
Tensile Shear Strength	2700 psi (Alum to Alum)

GENERAL INFORMATION:

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

HOW TO USE:

1. Carefully clean and dry all surfaces to be bonded.
2. Apply AA-BOND 201 completely mixed adhesive to the prepared surfaces, and gently press these surfaces together.
Contact pressure is adequate for strong, reliable bonds; however, maintain contact until adhesive is completely cured.
3. Some separation of components is common during shipping and storage. For this reason, it is recommended that the contents of the shipping container be thoroughly mixed prior to use.
4. Some ingredients in this formulation provided may crystallize when subjected to low temperature storage. A gentle warming cycle of 52°C for 30 minutes prior to mixing components may be necessary. Crystallized epoxy components do not react as well as liquid components and should be re-dissolved prior to use for best results.

AVAILABILITY:

This epoxy can be supplied in many different packages.

Atom Adhesives

Email: info@atomadhesives.com

200 Allens Ave, Providence, RI 02903

Phone: (888) 522-6742 - Fax: (877) 522-6742